



Green Synthesis of Zinc Oxide Nanoparticles Using Clove Oil Extract (*Syzygium aromaticum*) and Evaluate their Antibacterial Activity against MRSA

Mays U. Hashim ^{a*} and Orooba M. S. Ibrahim ^b

^a Department of Physiology, Biochemistry and Pharmacology College of Veterinary Medicine, University of Al-Qasim Green, Babylon, Iraq.

^b Department of Physiology, Biochemistry and Pharmacology, College of Veterinary Medicine, University of Baghdad, Baghdad, Iraq.

Authors' contributions

This work was carried out in collaboration between both authors. All authors read and approved the final manuscript.

Article Information

DOI: 10.56557/UPJOZ/2024/v45i43911

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://prh.mbimph.com/review-history/3235>

Original Research Article

Received: 09/12/2023

Accepted: 12/02/2024

Published: 17/02/2024

ABSTRACT

There is a crucial need for the development of effective antimicrobial agents due to the rising incidence of hospital-acquired bacterial infections caused by multidrug-resistant microbes, leading to significant mortality and morbidity worldwide. Therefore, the current study aimed to synthesize zinc oxide nanoparticles (SaZnONPs) using clove extract through an environmentally friendly technique and to investigate their antibacterial activity against MRSA (*Staphylococcus aureus*).

*Corresponding author: Email: hamza.hashim@vet.uoqasim.edu.iq, hamza14shukri72@gmail.com;

Clove extract acts as both a capping and reducing agent in the formation of ZnO-NPs. The formation of SaZnONPs was confirmed using various analytical techniques. Initially, clove extract was incubated with a zinc nitrate solution, and the subsequent change in color of the solution indicated the reduction of zinc nitrate ions to ZnO nanoparticles. UV-visible spectroscopy revealed a surface plasmon resonance band of SaZnONPs at 329.26 nm. Additionally, SEM imaging indicated that the nanoparticles had an average size of 41 nm and exhibited a spherical shape. The antibacterial activity of SaZnONPs was evaluated against MRSA using agar well diffusion and minimum inhibitory concentration assays. The phytochemicals present in clove extract facilitated the synthesis of stable ZnO-NPs, demonstrating promising antibacterial properties.

Keywords: SaZnONPs; plasmon resonance; clove extract; MRSA.

1. INTRODUCTION

Staphylococcus aureus (MRSA) is a significant human pathogen that causes a number of clinical infections [1]. The rise of multi-drug resistant strains like Methicillin-Resistant *Staphylococcus aureus* (MRSA) in community and hospital settings has made treating infections caused by *S. aureus* very difficult in recent decades [2,3]. The *mecA* or *mecC* gene, which encodes a penicillin-binding protein (PBP2a) or (PBP2ALGA) with a poor affinity for β -lactams, is the cause of methicillin resistance [4]. The demand for the creation of novel and efficient antibiotic alternatives has increased due to the emergence, dissemination, and durability of resistance to various antimicrobials. The development of nanotechnology have considerable potential of nanomaterials as antimicrobial agents. Compared to conventional antibiotics, nanomaterials offer a wider range of microbicidal activity. [5]. Among the most promising metallic nanomaterials, ZnO nanoparticles have been identified. Because ZnO-NPs are safe and stable for human cells, there has been an increase in interest in them as effective antibacterial agents in recent years [6, 7]. Biosynthesis of metal and metal oxide NPs with plant extraction is an innovative branch of nano biotechnology, which has been recognized depend on green chemistry [8]. Because plants contain carbohydrates, proteins, enzymes, and phytochemicals like phenols, terpenoids, ketones, aldehydes, and amides that are responsible for the spontaneous reduction of ions, it is actually possible to create inorganic NPs using plant extracts and their derivatives [9]. The most popular processes for creating ZnO NPs are hydrothermal synthesis and vapor-liquid-solid synthesis. Due to their non-hazardous, affordable, biodegradable, and environmentally benign properties, microorganisms, phyto extracts, and natural biomolecules have recently been used in the

production of nanoparticles [10,11]. *Syzygium aromaticum* (clove) is a member of the Myrtaceae plant family and has fragrant dried flower buds. In addition to glycosides and flavonols, clove also includes 10% fixed oil, 15-20% essential oil, 6-7% non-essential ether extract, and 13% tannin. [12]. It possesses antibacterial and antioxidant properties. In the commercial world, they are employed in the production of the fragrance and pharmaceuticals industry [13]. Clove essential oil's main ingredient, eugenol (4-allyl-2-methoxyphenol), has strong antibacterial, antioxidant, and insecticidal properties [14]. The current study illustrated an environmentally acceptable method for making zinc oxide nanoparticles (ZnO NPs) utilizing clove (*Syzygium aromaticum*) extract. This work was aimed to Biosynthesis of SaZno nanoparticles using plants, and investigate the antibacterial activity of the ZnO nanoparticles which are obtained by clove extract in-vitro.

2. MATERIALS AND METHODS

2.1 Plant Extract Preparation

2.1.1 Collection of plant

The origin of *S. aromaticum* that was purchased from a resident market.. All amount of clove buds cleaned three times with distilled water, disinfected with 5% sodium hypochlorite solution (NaOCl), and then allowed to dry. Using a mechanical mortar, the dried plant was ground into powder. The hydro-distillation extraction was performed by clevenger equipment. The amount of *Syzygium aromaticum* L. used for hydro-distillation was 200 g.

2.1.2 Preparation of clove oil (*Syzygium aromaticum*)

Clove oil was extracted from dry buds using hydro-distillation (water distillation) by Clevenger apparatus. Two hundred gram of dried buds

were taken and completely cleaned with double-distilled (DD) water to remove dust particles, then dried outside in the sun and placed in 1000ml glass flask, 500 ml of distilled water was placed. The flask was joined to the machine and the operation continue for 3 hours. The flask was placed in a heating mantle and electrically heated. The temperature of the flask was first raised progressively to 100°C from a starting point of roughly 80°C. The extraction procedure continuous at this temperature until no further droplets of oil was coming out of the condenser. The oil was collected after isolating the water , and to increase the water disposal a little of anhydrous sodium sulfate was used. The extract oil was kept in the refrigerator at a temperature of 4°C. [15].

2.1.3 Preparation of SaZnO nanoparticles

SaZnO nanoparticles were created using green synthesis method according to [16] with slight alteration. In a beaker with 300 ml of deionized water, 20 mg of Zn(NO₃)₂ was dissolved with a stirring for ten minute using magnetic stirrer. Then, 50mL of clove extract was added slowly into the beaker containing the Zn(NO₃)₂ solution under stirring condition and controlled pH above 9, until yellow color solution was obtained. A prepared organic phase of ethanol was made and added to the mixed solution in the glass beaker. The resulting suspension was centrifuged at 14,000 rpm after being filtered (using Whatman filter paper 1) to remove any precipitated materials. The solution was placed in a 20 ml beaker, transported straight to an ultrasonicator, and the emulsion was sonicated for five minutes at a power of 100 W and a frequency of 42 kHz.

2.2 Separation and Identification of Sa ZnO Nanoparticles

2.2.1 UV-Vis spectra analysis

Using UV-Vis spectrophotometry, the zinc oxide nanoparticles were evaluated for their maximum absorbance. UV-vis spectrum: sample of 0.2 gm of ZnONPs was taken, and the absorption was measured using a scanning spectrophotometer at intervals of 0.5 in the wave length range from 200 to 1100 nm. The peak increase positively with increase reaction time of ZnONPs synthesis [17].

2.2.2 Scanning electron microscopy (SEM)

The structural morphology of zinc oxide nanoparticles was examined and measured by

Scanning Electron Microscopic (SEM). The shape and size of synthesized SaZnONPs. were examined at advanced nano search center by using Scanning Electron Microscopy (SEM)[18].

2.3 Particle Size Distribution

A partical size analyzer was used to determine the particle size distribution (polydispersity index and mean diameter)(Malvern Instruments, Worcestershire, United Kingdom). It exploited the Mie theory of light, which says that the size of any particles present is related to the scattering pattern created when light passes through a sample [19]. SaZnO nanoparticles Before being examined in a size analyzer, the sample was treated in a sonicator water bath at 35C for 30 min. to prevent particle aggregation. The outcomes were monitored on a computer screen.

2.4 Antibacterial Activity of SaZnO-NPs

2.4.1 Isolation and characterization of bacterial isolates

Collection of specimens and bacterial identification were done by selecting five samples of pathogenic bacteria *Staphylococcus aureu* (MRSA strain). These samples were obtained from Microbiology lab at College of VET medicine / University of Baghdad. Samples were inoculated on nutrient agar and blood agar and then incubated at 37°C overnight below aerobic-circumstances. Many of these isolates were established for microscopic morphological, cultural and biochemical studies.

2.5 Preparation of Standard Bacterial Suspension

By comparing to the Standard McFarland solution (0.5), the quantity of MRSA bacteria in each milliliter of the stock suspension was standardized [20]. Briefly, bacterial suspension equivalent to 0.5 McFarland (1.5×10^8 CFU /ml) was arranged from overnight bacterial culture. The absorbance of this index was 0.136 as noted by spectrophotometer at a wave length of 450 nanometer. 0.1 ml of the prepared bacterial suspension was diluted in 14.9 ml of Mueller-Hinton broth and incubated at 37 °C for 1 hr. to obtain 10^6 CFU/ml bacterial suspensions [21,22].

2.6 Measurement of Antimicrobial Activity of SaZnO-NPs was done by Three Methods

2.6.1 Agar well diffusion methods

The agar well diffusion method was taken on according to [23], for evaluating the antibacterial activity of SaZnO-NPs against MRSA. Standardized bacterial suspension (1.5×10^8 cfu/ml) of *S. aureus* was carefully mixed with sterile Mueller Hinton agar. 25 ml of the sterile agar was dispersed into sterile Petri dishes and left for 10 minutes in room temperature to allow to dry, and six mm. diameter wells were bored in the agar. The SaZnO-NPs was reconstituted in distilled water to a concentration from 5 µg/ml to 0.312 µg/ml and then 100 µl was added to wells. The plates were at 37 °C for 24 hours after allowing the extract to diffuse into the agar at room temperature. Thereafter, the diameter of the inhibitory zone was measured to the closest millimeter (mm).

2.6.2 Microtiter plate Dilution

SaZnO-NPs (10 mg/ml) was made in Mueller-Hinton broth, from this broth, two folds dilution was downgraded from 40 µg for clove oil in U-shape (200 µl well capacity) 96 well micro-titer plate, Each well was inoculated with 100 µl of 10^6 CFU/ml *S. aureus* and incubated on 37°C for 24hrs. For colorimetric identification of bacterial growth, 15 µl of 0.125% triphenyltetrazolium chloride dye was added to each well of the test and re-incubated for two hrs. [24] in order to determined MIC and MBC which was determined as the lowest concentration of extracts kill the bacteria [25].

2.7 In-vitro Time Kill Curve Kinetic

The time-kill curve assay of SaZnO-NPs against MRSA were based on the National Committee for Clinical Laboratory Standards [26]. Briefly, bacterial suspension prepared as mention

before and the Clove extract had been dissolved in Mueller-Hinton broth to prepare 10 mg/ml stock solution, after that, clove extract concentrations from 4x MIC to 0.25x MIC were prepared. Bacterial colonies were calculated at 0, 1, 2, 4, 6, and 24 h through the incubation time by making serial dilutions and spreading of 20 µl of each dilution on Mueller-Hinton agar plate (triplicate); colonies range 30-300 CFU/plate was accepted [27].

The trapezoidal method was used to estimate the area under the time-kill curve of concentration of SaZnO-NPs as below [28]:

$$AUC_{kill} = \sum \left(\frac{\log(C_n) + \log(C_{n+1})}{2} \cdot \Delta t \right)$$

Where the AUC_{kill} is the area under the killing curve of SaZnO-NPs, $\log(C_n)$ is the logarithm of a specific concentration at a specific time, $\log(C_{n+1})$ is the logarithm of the next concentration while (Δt) resemble the difference between their times.

2.8 Statistical Analysis

The Statistical Analysis System- SAS [29] program was used to detect the effect of difference factors in study parameters. Least significant difference –LSD test (Analysis of Variation-ANOVA) was used to significant compare between means in this study.

3. RESULTS

3.1 Nanoparticles Characterization

3.1.1 Visual observation

The color shift from dark yellow to light yellow after combining with clove extract is the first sign of the creation of SaZnO nanoparticles as shown in (Fig 2).




Fig. 1. The changing in color of clove extracts from dark yellow to light yellow
(a) Clove extract solution (b) Extract after reaction with Zn nitrate solution to form ZnO nanoparticles




Fig. 2. UV-VIS absorbance spectroscopy for SaZnO nanoparticles from clove extract

3.2 UV-Visible Spectroscopy

UV-Vis spectroscopy was used to assess the absorbance of a solution of SaZnO nanoparticles; the results showed that the SaZnO nanoparticles' highest absorbance occurred at the absorbance peak of 329.26 nm. as show in (Fig 2).

3.3 Scanning Electron Microscopy (SEM)

Fig 4 illustrates a typical SEM picture of the produced SaZnO NPs, which appear different magnifications of ZnO nanoparticles. This images makes it obvious that there are spherical to hexagonal-shaped particles with a grain size of 41.4 nm in aggregated states.




Fig. 3. Scanning Electron Microscopy image of particle size and morphology of SaZnONPs




Fig. 4. Particle size of SaZnO NPs

3.4 Particle Size Analyzer

The size of the nanoparticles was measured using a size analyzer that relied on dynamic light scattering. The distribution of size analysis showed that the synthetic SaZnONPs had an effective diameter of about 41 nm. (39.7 ± 4.1) as show in (Fig 4)

Biosynthesis of zinc oxide nanoparticles from clove extract in this study was identified by clearly changing in color as a step was showing in Fig 1. The SPR (surface plasmon resonance)

in the metal nanoparticles is indicated by the color change[30]; After the clove extract was incubated with the zinc nitrate solution, a color change was noticed, which is proof that the zinc nitrate ion was reduced to ZnO nanoparticles. Bio-reduction is the process of reducing metal ions to metal nanoparticles with the help of phytochemicals such polyphenols, polysaccharides, alkaloids, vitamins, and amino acids. Flavonoids act as reducing elements for metal ions. However, the functional groups of flavonoids are what cause the formation of nanoparticles [17].

Fig (2) clarified the UV-visible spectra of prepared ZnONPs from clove extract. SaZnO nanoparticles' absorbance peak at 329.26 nm revealed that this wavelength's significant absorption peak is caused by zinc oxide's band-gap absorption, which is the result of electrons being removed from its valence band and transferred to its conduction band[31]. Zinc oxide nanoparticles exhibit good UV absorption in the range of 200 to 400 nm, making them useful for medical applications like sunscreen or antiseptic ointments [32].

To describe the size, form, morphology, and distribution of created nanoparticles, the SEM analysis is used. Many sizes and shapes were produced through the green synthesis of SaZnO NPs from clove extract, but the most common shape was spherical with a diameter of about 41 nm. These nanoparticle forms were consistent with the research of Vahidi et al. [33], who used *Pelargonium* leaf extract to create ZnO NPs with the same morphological characteristics. This test suggests that the SaZnO -NPs employed in this investigation are high-quality materials. Our results are in coordination with earlier studies [34].

The SaZnONPs size was calculated via dynamic light scattering. The average particle size, according to the size of the nanoparticles dispersion analysis, was 41.4 nm. (Fig 4). Small particles are known to be more effective than large ones in terms of NP activity, which is influenced by their size[35]. Numerous earlier studies revealed that NPs' activity varied depending on their particle size [36].

3.5 Antibacterial Results of SaZnO-NPs

The multidrug resistant strains of *S. aureus* are increasing, making the treatment more challenging. The prevalence of MRSA among *S. aureus* isolates is the highest over the world. The results showed that the concentration 0.312 µg/ml SaZnO nanoparticles were effective to prevent MRSA from growing, these concentrations were shown to have a positive value that inhibit the growth 0.625 µg/ml of SaZnO nanoparticles killed MRSA so it considered as the (MBC) that tested in micro-dilution assay.

The plant extracts may temporarily exhibit an action against infections, but they are susceptible to destruction after a while due to the presence of many chemical components in their structure [37], however after usage in the biological

synthesis of nanoparticles, the active substance including proteins, vitamins, enzymes, alcohol and amino acids compounds that present in the plant extract and are responsible for the development of the nanoparticles act as reducing and covering substance for many months [38].

According to the study by [39] ZnO-NPs have broad-spectrum antibacterial properties and can even eliminate MRSA and other drug-resistant pathogenic bacteria. The possible mechanisms of action of ZnO-NPs against bacteria include the following: (a) excessive production of reactive oxygen species by bacteria, (b) disruption of key enzymes in the respiratory chain due to damage to microbial plasma membranes; (c) metal ion accumulation in microbial membranes; (d) inhibition of metabolic processes by electrostatic attraction between nanoparticles of metal and microbial cells; and (e) suppression of microbial proteins/enzymes through increased production of H₂O₂. [40].

Strong anti-microbial properties are possessed by metal nanoparticles, particularly ZnO NPs; the mechanism for this is that ZnO-NPs will produce hydrogen peroxides (H₂O₂), and these peroxides will disturb the lipid and protein bilayers, which will destroy bacterial cells [41]. In addition, another antimicrobial action of ZnO-NPs involves the production of reactive oxygen species (ROS) and accumulation of the nanoparticles in the cytoplasm which causes cell death. Bacterial DNA proteins and lipids will be damaged by the generated ROS, leading to cell death [42, 43].

On other hand, the concentration and size of ZnO nanoparticles significantly influenced bacterial growth. Therefore, ZnO-NPs may have a size-dependent antibacterial effect. Nanoparticles with smaller size can penetrate through the microbial cell membrane more easily and enter into the mitochondria leading to mitochondrial oxidative stress and apoptosis, thus inhibits growth of the cell and promotes its death [43].

3.6 Sensitivity Assay

Different concentrations of SaZnONPs was using in agar well diffusion methods, resulting in different sizes of inhibition zone against methicillin resistance *staphylococcus aureus*. The sizes of inhibition zones were different according to concentration of the SaZnONPs. Results indicated that MRSA strain were

sensitive significantly ($P < 0.05$) to SaZnONPs in a dose dependent concentration 5, 2.5, 1.25, 0.625 and 0.312 $\mu\text{g/ml}$. Increasing in the diameter measurement of zone of inhibition in MRSA growth was proportionally related to SaZnONPs concentrations, (Table 1), (Fig 5).

The results of SaZnONPs showed that the inhibitory effect increased as the concentration increased and reached its peak inhibition zone of 25.0mm at 5 $\mu\text{g/ml}$. this is in line with [44] who observed that 1% ZnO-NP solution exhibited maximum inhibition of the zone against *Staphylococcus aureus* (21 mm). while Irfan *et al.*, [45] who used *Moringa oleifera* for synthesis ZnO-NPs and detected good activity against methicillin-resistant *Staphylococcus aureus* (MRSA) at concentrations higher than as 30 μg , 20 μg , and 10 μg) and produced inhibition zone in the range of 17, 12 and 6 mm. respectively.

In general Pati *et al.* (46) have demonstrated that zinc oxide nanoparticles damage the integrity of

bacterial cell membranes, decrease the hydrophobicity of cell surfaces, and suppress the transcription of oxidative stress-resistance genes in bacteria. By promoting the formation of ROS, they improve intracellular killing of bacteria. These nanoparticles prevent the development of biofilms and inhibit pathogens' hemolysin toxin from inducing hemolysis.

In order to demonstrate the size-dependent antibacterial activity of ZnO-NPs, it has been stated that the smaller size of ZnO-NpS has stronger antibacterial activity than microscale particles [47] and these in accordance with our results as we obtained nanoparticles in size 41nm. The small size of ZnO-NPs has the ability to inter the microbial cells because of their high surface area to volume ratio [48]. Therefore, smaller ZnO-NPs are more potent antibacterial agents than the larger one [49]. *S. aureus* growth is inhibited when the size is 12 nm, but as the size above 100 nm, the inhibitory effect is decreased [50].

Table 1. In-vitro antibacterial efficacy of SaZnO-NPs in different concentrations against MRSA (measured as the diameter of the inhibitory zone in millimeters)

Groups Conc.	Con.($\mu\text{g/ml}$)				
	5 $\mu\text{g/ml}$	2.5 $\mu\text{g/ml}$	1.25 $\mu\text{g/ml}$	0.625 $\mu\text{g/ml}$	0.312 $\mu\text{g/ml}$
Sa ZnO-NPs	25.0 $\pm$ 0.97	19.0 $\pm$ 0.77	17.0 $\pm$ 0.82	14.0 $\pm$ 0.57	12.0 $\pm$ 0.61
	A a	A b	A ab	A bc	A c
LSD value	3.337				

Values represent mean $\pm$ S.E
Different letters denoted a significant difference ($p \leq 0.05$) among the groups




Fig. 5. Proportional relationship between different concentration of SaZnO-NPs, Clove oil and the mean of inhibition zone (mm) against MRSA

According to this study's finding we can say that ZnO-NPs reinforced with clove extract and can be utilised as an alternative to commercially available antibacterial agents. Since applying plant extract to produce metal oxide, significant benefits have been obtained because of the production of the functional molecules which reduce metal ions during synthesis of nanoparticles [51].

3.7 Time Kill Curve Kinetics

The time-kill curve kinetics of SaZnO nanoparticles are based on the highest MIC recorded from the micro-dilution assay which were 0.312 µg/ml for the MRSA strain. The concentrations used *in vitro* study were 0.25x MIC, 0.5x MIC, 1x MIC, 2x MICs, 4x MICs Fig. 6. SaZnONPs showed bactericidal activity at concentration of 4xMICs, 2xMICs by reducing ≥ 3 log₁₀ of the total number of CFU/ml of MRSA at 4 and 6 hr respectively as show in (Fig 7) in comparison to control, 0.25x MIC and 0.5x MIC; on the other hand, 1x MIC for two agents showed

a drop in growth curve at 1st six hours. Then, there was continued inhibition of growth as reported at the 24th hour (Fig 7).

The area under the time of killing curve of SaZnO nanoparticles calculated and compared to control inoculum growth rate, and the difference in the area under the curve values among different treatments were set as an endpoint whereas the lowest area under the curve refers to the highest bactericidal effect as reported in the (Table 2).

The results showed that all of 2xMICs and 4xMICs achieved the highest significant bactericidal effect ($P \geq 0.05$) in comparison to other treatments. The 1xMIC concentration achieved purely bacteriostatic effect ($P \geq 0.05$) in comparison to all concentrations and control groups; both of 0.5xMIC and 0.25xMIC failed to achieves a significant bacteriostatic or bactericidal effect ($P \leq 0.05$) in comparison to 1xMIC, 2xMIC and 4xMIC.




Fig. 6. Sensitivity of MRSA to different concentrations of SaZnO -NPs

Table 2. Area under the time-kill curve of Sa ZnO NPs against MRSA ($h^* \log$ CFU/ml)

Antibacterial	Control	0.25xMIC	0.5xMIC	1xMIC	2xMIC	4xMIC
Sa ZnONPs	121.12	115.71	76.15	49.12	20.37	11.77
MIC=0.312 µg\ml	± 0.25	± 0.31	± 0.41	± 0.44	± 0.52	± 0.14
	A	A	B	C	D	D
LSD	9.1*					

Values represent mean $\pm$ S.E

Different letters denoted a significant difference ($p \leq 0.05$) among the groups




Fig. 7. Time kill curve kinetics of SaZnO -NPs against MRSA

Time killing curve kinetic is a combined and extensive tool to assess both bacteriostatic and bactericidal effects of the antibiotics; it depends on the change in the logarithmic number of bacterial colonies through the defined chronological pattern [52]. More accurate descriptions of antimicrobial activity are provided by a measure of bacterial killing (kill kinetics) than by the MIC, and it has also shown better sensitivity developments to physicians than disc diffusion methods [53; 54]. When the concentration was increased more than two fold in MICs, each of 2xMICs, and 4xMICs concentrations of SaZnO nanoparticles showed a distinguished bactericidal effect at the 6 hr and 4 hrs respectively. These is nearly as same as what reported by Steffy et al [55], where they found that ZnO nanoparticles at 2xMICs killed more than 99.91% of *S. aureus* ATCC at the same time that we report considering the difference in the isolates that were used in studies. At higher ZnO-NPs concentrations (2 and 4x MIC), noticeable bactericidal activity is seen. After 6 hours of being subjected to ZnO-NPs, the bacteria are completely destroyed.

In the present study, it was also found that the greater concentration of SaZnO NPs, the shorter the time are required for the bactericidal action on the tested bacteria. Likewise, Hoseinzadeh et al., [56] reported that the time killing for *S. aureus* and *E. coli* at 2xMIC was 3 and 6 h respectively.

Time killing kinetic of SaZnO nanoparticles against *MRSA* was concentrations and time dependent [57-59]. This in turn suggests a more rational basis for establishing the ideal dose for antimicrobial treatment regimens., in order to prevent the development and spread of antimicrobial resistance.

4. CONCLUSIONS

The ability of *S. aromaticum*'s aqueous extract to create ZnONPs has been established. Compared to the traditional physical and chemical metal oxide NP fabrication methods, the green synthetic approach for the synthesis of ZnO NPs uses clove extract as a natural reducing and stabilizing agent, making this synthesis method simple, energy-efficient, and cost-effective. The reduction of zinc nitrate to ZnONPs was approved by UV-visible spectrophotometer, SEM, particle size analyzer and zeta potential analyzer techniques. In addition, SaZnO-NPs showed strong antibacterial effectiveness. As a result, they could be employed as an antibacterial agent and a viable alternative to traditional antibiotics.

ACKNOWLEDGEMENTS

Authors acknowledge to the Department of Physiology and Pharmacology, College of

Veterinary Medicine, University of Baghdad, Baghdad, Iraq. Ministry of Science and Technology Laboratories / Department of Materials Research for support.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

1. Chambers HF, DeLeo FR. Waves of resistance: *Staphylococcus aureus* in the antibiotic era. *Nature Reviews Microbiology*. 2009;7(9):629-641.
2. Taylor TA, Unakal CG; 2017. Available: *Staphylococcus aureus*.
3. Jasim Al-Jumaili MA, Saeed Ibrahim OM. Pharmacodynamic Properties Of Meropenem Against *Staphylococcus Aureus*. *Biochemical & Cellular Archives*. 2021;21(1)
4. Kim C, Milheiro C, Gardete S, Holmes, M. A., Holden, M. T., de Lencastre, H., & Tomasz, A. Properties of a novel PBP2A protein homolog from *Staphylococcus aureus* strain LGA251 and its contribution to the β -lactam-resistant phenotype. *Journal of Biological Chemistry*. 2012;287(44):36854-36863.
5. Raghunath A, Perumal E. Metal oxide nanoparticles as antimicrobial agents: a promise for the future. *International Journal of Antimicrobial Agents*. 2017;49(2):137-152.
6. Tayel AA, ELTRAS WF, Moussa S, EL-BAZ AF, Mahrous H, Salem MF, Brimer L. Antibacterial action of zinc oxide nanoparticles against foodborne pathogens. *Journal of Food Safety*. 2011; 31(2):211-218.
7. Król A, Pomastowski P, Rafińska K, Railean-Plugaru, V, Buszewski B. Zinc oxide nanoparticles: Synthesis, antiseptic activity and toxicity mechanism. *Advances in Colloid and Interface Science*. 2017;249, 37-52.
8. Ahmadi O, Jafarizadeh-Malmiri H, Jodeiri N. (). Eco-friendly microwave-enhanced green synthesis of silver nanoparticles using *Aloe vera* leaf extract and their physico-chemical and antibacterial studies. *Green Processing and Synthesis*. 2018;7(3):231-240.
9. Ayad ZM., Ibrahim OMS, Omar LW. Biosynthesis and characterization of silver nanoparticles by *Silybum marianum* (silymarin) fruit extract. *Adv. Anim. Vet. Sci*. 2019;7(2):122-130.
10. Wang P, Jiang L, Han R. Biosynthesis of zinc oxide nanoparticles and their application for antimicrobial treatment of burn wound infections. *Materials Research Express*. 2020;7(9):095010.
11. Ibrahim OMS, Saliem AH, Salih SI. Antibacterial activity of silver nanoparticles synthesized by *Cinnamon zeylanicum* bark extract against *Staphylococcus aureus*. *Al-Anbar J. Vet. Sci*. 2016;9(1):22-36.
12. Chatterjee D, Bhattacharjee P. Use of eugenol-lean clove extract as a flavoring agent and natural antioxidant in mayonnaise: product characterization and storage study. *Journal of food science and technology*. 2015;52:4945-4954.
13. Ali BM, Ibrahim O. Antifungal activity of clove (*Syzygium aromaticum*) Essential Oil Extract against Induced Topical Skin Infection by *Candida albicans* in Mice in vivo. *The Egyptian Journal of Hospital Medicine*. 2023;91(1):3855-3861.
14. Anvarinezhad M, Javadi A, Jafarizadeh-Malmiri H. Green approach in fabrication of photocatalytic, antimicrobial, and antioxidant zinc oxide nanoparticles—hydrothermal synthesis using clove hydroalcoholic extract and optimization of the process. *Green Processing and Synthesis*. 2020;9(1):375-385.
15. Taraj K, Andoni A, Fatos Y, LLI Ariana, YI. LI, Hoxha R, Ilupa J, malollari I. Spectroscopic investigation of *Syzygium aromaticum* L. Oil by water distillation extraction. *Journal of International Environmental Application and Science*. 2020;15(2):122-126.
16. Jayachandran A, Aswathy TR, Nair AS. Green synthesis and characterization of zinc oxide nanoparticles using *Cayratia pedata* leaf extract. *Biochemistry and Biophysics Reports*. 2021;26:100995.
17. Husain WM, Araak JK, Ibrahim OM. Green synthesis of zinc oxide nanoparticles from (*Punica granatum* L) pomegranate aqueous peel extract. *The Iraqi Journal of Veterinary Medicine*. 2019;43(2):6-14.
18. Salih AN, Ibrahim OM, Eesa MJ. Antibacterial activity of biosynthesized silver nanoparticles against *Pseudomonas aeruginosa* in vitro. *The Iraqi Journal of Veterinary Medicine*. 2017;41(1):60-65.

19. Levoguer C. Using laser diffraction to measure particle size and distribution. Metal Powder Report. 2013;68(3):15-18.
20. Ibrahim OM, Saliem AH, Salih SI. Antibacterial activity of silver nanoparticles synthesized by Cinnamon zeylanicum bark extract against Staphylococcus aureus. Al-Anbar J. Vet. Sci. 2016;9(1):22-36.
21. Dominguez MC, de La Rosa M, Borobio MV. Application of a spectrophotometric method for the determination of post-antibiotic effect and comparison with viable counts in agar. J Antimicrob Chemother. 2001;47(4):391-8.
22. Shakeel S, Khan U, Zeeshan A, Aqib Z, Somia G. *In vitro* evaluation of antimicrobial activity of Entoban Syrup; a polyherbal formulation. World Journal of Pharmaceutical Research. 2015;4(5):504-511.
23. Salih AN, Ibrahim OM, Eesa MJ. Antibacterial activity of biosynthesized silver nanoparticles against Pseudomonas aeruginosa *In vitro*. The Iraqi Journal of Veterinary Medicine. 2017;41(1):60-65.
24. Mohammed SA, Ibrahim O. Pharmacodynamics analysis of fosfomycin against multidrug resistant *E. coli* O157:H7 isolated from urinary tract infection. Biochemical & Cellular Archives. 2022; 22(1).
25. Al-Mizraqchi AS. Anti-microbial activity of Green Tea Extracts and Nicotine on the Growth, Biofilm Formation of Sali-vary Mutans Streptococci (*In-vitro* study). Journal of the Faculty of Medicine Baghdad. 2023;65(2).
26. NCCLS, National committee for clinical laboratory standards. approved standard M7-A5: Methods for Dilution Antimicrobial Susceptibility Test for Bacteria that Grow Aerobically, 5th Ed; 2000.
27. Shwaish MM, Ibrahim O. Pharmacodynamics analysis of meropenem against klebsiella pneumonia isolated from Covid-19 patient. Biochemical & Cellular Archives. 2022; 22(1).
28. Chiou WL. Critical evaluation of the potential error in pharmacokinetic studies of using the linear trapezoidal rule method for the calculation of the area under the plasma level-time curve. Journal of pharmacokinetics and biopharmaceutics. 1978;6:539-546
29. SAS S. Statistical Analysis System, User's Guide. Statistical. Version 9. SAS. Inst. Inc. Cary. NC USA. 2018.
30. Lee S, Najiah M, Wendy W, Nadirah M. Chemical composition and antimicrobial activity of the essential oil of Syzygium aromaticum flower bud (Clove) against fish systemic bacteria isolated from aquaculture sites. Frontiers of Agriculture in China. 2009;3:332-336.
31. Zak AK, Abrishami ME, Abd WH. Majid, Ramin Yousefi, SM Hosseini. Ceram Int. 2011;37:393-398.
32. Zak AK, Razali R, Majid WA, Darroudi M. Synthesis and characterization of a narrow size distribution of zinc oxide nanoparticles. International Journal of Nanomedicine. 2011;1399-1403.
33. Vahidi A, Vaghari H, Najian Y, Najian MJ, Jafarizadeh-Malmiri H. Evaluation of three different green fabrication methods for the synthesis of crystalline ZnO nanoparticles using Pelargonium zonale leaf extract. Green Processing and Synthesis. 2019; 8(1):302-308.
34. Pillai AM, Sivasankarapillai VS., Rahdar A, Joseph J, Sadeghfaz F, Rajesh K, Kyzas, GZ. Green synthesis and characterization of zinc oxide nanoparticles with antibacterial and antifungal activity. Journal of Molecular Structure. 2020;1211:128107
35. Ghotaslou R, Bahari Z, Aliloo A, Gholizadeh P., Eshlaghi BS. The *In vitro* effects of silver nanoparticles on bacterial biofilms. Journal of Microbiology, Biotechnology and Food Sciences. 2021; 1077-1080.
36. Martínez-Castañón GA, Nino-Martinez N, Martinez-Gutierrez F, Martinez-Mendoza, JR, Ruiz F. Synthesis and antibacterial activity of silver nanoparticles with different sizes. Journal of Nanoparticle Research. 2008;10(8):1343-1348.
37. Negi PS. Plant extracts for the control of bacterial growth: Efficacy, stability and safety issues for food application. International Journal of Food Microbiology. 2012;156(1):7-17.
38. Mustapha T, Misni N, Ithnin NR, Daskum AM, Unyah NZA review on plants and microorganisms mediated synthesis of silver nanoparticles, role of plants metabolites and applications. International Journal of Environmental Research and Public Health. 2022;19 (2):674.
39. Banerjee S, Vishakha K, Das S, Dutta M, Mukherjee D, Mondal J, Ganguli A.

- Antibacterial, anti-biofilm activity and mechanism of action of pancreatin doped zinc oxide nanoparticles against methicillin resistant *Staphylococcus aureus*. *Colloids and surfaces B: Biointerfaces*. 2020;190: 110921.
40. Nisar P, Ali N, Rahman L, Ali M, Shinwari, ZK. Antimicrobial activities of biologically synthesized metal nanoparticles: an insight into the mechanism of action. *JBIC Journal of Biological Inorganic Chemistry*. 2019; 24:929-941.
41. Dutta RK, Nenavathu BP, Gangishetty M. K. Reddy AVR. Studies on antibacterial activity of ZnO nanoparticles by ROS induced lipid peroxidation. *Colloids and Surfaces B: Biointerfaces*. 2012;94:143-150.
42. Akhtar MJ, Ahamed M, Kumar S, Khan M. M, Ahmad J, Alrokayan SA. Zinc oxide nanoparticles selectively induce apoptosis in human cancer cells through reactive oxygen species. *International Journal of Nanomedicine*. 2012;845-857.
43. Xia T, Kovochich M, Nel AE. Impairment of mitochondrial function by particulate matter (PM) and their toxic components: implications for PM-induced cardiovascular and lung disease. *Frontiers in Bioscience-Landmark*. 2007;12(4):1238-1246.
44. Faisal S, Jan H, Shah SA, Shah S, Khan A, Akbar MT, . Syed S. Green synthesis of zinc oxide (ZnO) nanoparticles using aqueous fruit extracts of *Myristica fragrans*: their characterizations and biological and environmental applications. *ACS Omega*. 2021;6(14):9709-9722.
45. Irfan M, Munir H, Ismail H. Moringa oleifera gum based silver and zinc oxide nanoparticles: Green synthesis, characterization and their antibacterial potential against MRSA. *Biomaterials Research*. 2021;25(1):17.
46. Pati R, Mehta RK, Mohanty S, Padhi A, Sengupta M, Vaseeharan B, & Sonawane, A. Topical application of zinc oxide nanoparticles reduces bacterial skin infection in mice and exhibits antibacterial activity by inducing oxidative stress response and cell membrane disintegration in macrophages. *Nanomedicine: Nanotechnology, Biology and Medicine*. 2014;10(6):1195-1208
47. Yamamoto O. Influence of particle size on the antibacterial activity of zinc oxide. *International Journal of Inorganic Materials*. 2001;3(7):643-646.
48. Onyszko M, Zywicka A, Wenelska K, Mijowska E. Revealing the Influence of the Shape, Size, and Aspect Ratio of ZnO Nanoparticles on Antibacterial and Mechanical Performance of Cellulose Fibers Based Paper. *Particle & Particle Systems Characterization*. 2022;39(6): 2200014.
49. Zhu X, Wang J, Cai L, Wu Y, Ji M, Jiang H, Chen J. Dissection of the antibacterial mechanism of zinc oxide nanoparticles with manipulable nanoscale morphologies. *Journal of Hazardous Materials*. 2022;430: 128436.
50. Jones N, Ray B, Ranjit KT, Manna AC. Antibacterial activity of ZnO nanoparticle suspensions on a broad spectrum of microorganisms. *FEMS Microbiology Letters*. 2008;279(1):71-76.
51. Rai M, Ingle A. Role of nanotechnology in agriculture with special reference to management of insect pests. *Applied Microbiology and Biotechnology*. 2012;94:287-293.
52. Mouton, p JW, Dudley MN, Cars O, Derendorf H, Drusano GL. Standardization of pharmacokinetic/pharmacodynamic; 2005. (PK/PD) terminology for anti-infective drugs: an update. *Journal of antimicrobial Chemotherapy*, 55(5), 601-607.
53. Mandal S, Mandal MD, Pal NK. Antibacterial potential of *Azadirachta indica* seed and *Bacopa monniera* leaf extracts against multidrug resistant *Salmonella enterica* serovar Typhi isolates. *Archives of Medical Science*. 2007;3(1):14-18.
54. Mandal S, DebMandal M, Saha K, Pal N. K. *In vitro* antibacterial activity of three Indian spices against methicillin-resistant *Staphylococcus aureus*. *Oman Medical Journal*. 2011;26 (5):319.
55. Steffy K, Shanthi G, Maroky AS, Selvakumar S. Enhanced antibacterial effects of green synthesized ZnO NPs using *Aristolochia indica* against Multi-drug resistant bacterial pathogens from Diabetic Foot Ulcer. *Journal of Infection and Public Health*. 2018;11(4):463-471.
56. Hoseinzadeh E, Alikhani MY, Samarghandi MR, Shirzad-Siboni M. Antimicrobial potential of synthesized zinc oxide nanoparticles against gram positive and gram-negative bacteria. *Desalination and Water Treatment*. 2014;52(25-27):4969-4976.
57. Okemo PO, Mwatha WE, Chhabra SC, Fabry W. The kill kinetics of *Azadirachta*

- indica A. Juss. (Meliaceae) extracts on Staphylococcus aureus, Escherichia coli, Pseudomonas aeruginosa and Candida albicans. African Journal of Science and Technology. 2001;2(2):113-118.
58. Amira A. Mohamed, Abeer A. Nassr, Sadeek A. Sadeek, Nihad G. Rashid, Sherif M. Abd El-Hamid, First Report on Several NO-Donor Sets and Bidentate Schiff Base and Its Metal Complexes: Characterization and Antimicrobial Investigation, Compounds. 2023;3:376-389.
59. Mohamed S. El-Attar, Sadeek A. Sadeek, Sherif M. Abd El-Hamid and Hazem S. Elshafie, Spectroscopic Analyses and Antimicrobial Activity of Novel Ciprofloxacin and 7-Hydroxy-4-methylcoumarin, the Plant-Based Natural Benzopyrone Derivative, Int. J. Mol. Sci. 2022;23L8019.

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:
<https://prh.mbimph.com/review-history/3235>